

ACRIFIX® 1S 0107 Quick Set

Solvent Cement

Product and Use

ACRIFIX® 1S 0107 Quick Set Solvent Cement is a thin-bodied, quick drying, colorless to slightly yellowish solvent adhesive (one-component) containing methylene chloride that will not blush.

Typical Values of Properties

Viscosity (Brookfield A/60/68°F/20°C):	≤ 15 cp
Density (86°F/20°C):	~1.22 g/cm ³
Color:	clear to yellowish; color does not affect bonding properties.
Flash point (Closed Cup):	No flash point
Solids Content	≤ 1 %
Storage stability:	2 years after filling, if stored correctly
Storage temperature	Max 86°F/30°C
Packaging materials	glass, tinplated steel or aluminum bottles (with inside coating)
Curing	physically, through evaporation and absorption in the bonded articles

Applications

ACRIFIX® 1S 0107 is used for making T-joints and bonding narrow areas of all grades of

uncross-linked ACRYLITE® products. crazing only occurs in parts with extreme internal stresses. ACRIFIX® 1S 0107 is not gap-filling. The bond is firm within a short time.

Safety Measures and Health Protection

Contains dichloromethane, a suspected carcinogen. Harmful if inhaled and swallowed; irritating to eyes, respiratory system, and skin. Do not breathe vapor or spray. Avoid contact with eyes and skin. Wear suitable protective gloves and clothing to avoid contact with skin. In operations where eye or face contact could occur, wear eye protection such as chemical splash-proof goggles or a face shield. In the event of contact with eyes, rinse immediately with plenty of water and consult a doctor. Keep away from heat, sparks, and flames. In case of fire and/or explosion, do not breathe fumes. Keep container closed and use adequate ventilation.

Bonding Technique

Secure the parts to be bonded in the desired position. Introduce ACRIFIX® 1S 0107 into the joint either from a glue dispenser or disposable syringe, and avoid bubble formation. It can be used for making T-joints and bonding narrow areas of ACRYLITE® cast and extruded sheet as well as ACRYLITE® Resist. It can be utilized in the same applications as most methylene chloride

based cements as long as proper precautions are observed. It will not fill gaps caused by unfinished edges. It is recommended that edges be either scraped or milled to produce a flat level cementing surface.

The resulting bond will be firm in a relatively short period of time depending on the substrate and will have high ultimate strength.

Normally, a sawn or milled edge of one article is bonded at a right angle to the original surface of another article. Avoid bonding in areas where a high stress level is to be expected (e. g. near pin gates or different wall thicknesses). The parts to be bonded must have a very accurate fit. Grooves and notches are not filled. Clean the areas to be bonded with ACRIFIX® TC 0030, petroleum ether or isopropyl alcohol before applying the adhesive. Either of two methods may be used:

a) Lock the two parts in position without adhesive and introduce ACRIFIX® 1S 0107 into the joint from a small nozzled bottle. The adhesive penetrates the joint by capillary action. For sheet thickness > 0.236", the parts should first be put together with the aid of shims (e.g. stainless steel wire, 0.004" – 0.020"). The shims are placed at right angles to the sheet edge and are pulled out after introduction of the adhesive.

b) The appropriate edge of one of the parts to be bonded is dipped into ACRIFIX® 1S 0107 and placed in contact with the second part after allowing sufficient time for solvent action. The holding time will be about 20 seconds for ACRYLITE® extruded (FF) sheet and about 60 seconds for ACRYLITE® cast (GP) sheet.

After the short holding time, the bond is locked in position and a pressure of at least 100 g/ cm² adherence is applied. When bonding sawn edges, bubble formation can be reduced by smoothing the edges prior to binding with fine, wet adhesive

paper (400–600 grit) or passing the edges over with a scraper and wiping them vigorously several times with a cloth soaked in ACRIFIX® 1S 0107 (wear protective gloves!)

Further Indications

1) The maximum pot life of ACRIFIX® 1S 0107 in an open dish is about 30 min because its composition changes by evaporation of predominately one component.

2) Whitening around the adhesive joint is due to water condensing from the air (especially if the room temperature is low).

Properties of Bonds

Initial bond:

ACRYLITE® extruded (FF): ~ 5 sec

ACRYLITE® cast (GP) sheet: ~ 30 sec

Time before processing:

Not within the first three hours.

Tensile shear strength:

Annealing increases the strength and also improves weather resistance.

Material (to itself)	Non-annealed	Annealed (at 180° F)
ACRYLITE® extruded	4060 +/- 725 psi	4785 +/- 725 psi
ACRYLITE® cast	3335 +/- 725 psi	4060 +/- 725 psi

Annealing

Crazing will occur if high internal stress from fabrication is not relieved. Internal stress can be minimized by careful fabrication and annealing before the cementing. To anneal ACRYLITE®

sheet, place it in an air circulating oven at 160–176°F for an hour for each millimeter of thickness (minimum of two hours). For more information, refer to ACRYLITE® Fabrication Technical Brief #12, Annealing.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Evonik Industries is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African, and Australian continents. © Evonik Cyro LLC. All rights reserved. Printed in the USA.

Evonik Cyro LLC
299 Jefferson Road, Parsippany, NJ 07054 US
Phone +1800 631 5384
www.acrylite.net www.acrylite-shop.com www.acrifix.com